

### Product Description

La GreenCote Plus is a elastomeric, water based aliphatic acrylate, silicon based coating with anti-carbonation property for exterior masonry or concrete surface. It has exceptional flexibility, breathability, sealing of cracks, UV resistance and adhesion characteristics to provide optimum protection to surfaces subject to thermal movement.

La GreenCote Plus is designed with 100% acrylic polymer and is the latest APEO free. The unique chemistry offers high scrub resistance and excellent stain resistance

#### Standard

Tested to ASTM D4541, ASTM D882, ASTM D 1653, ASTM D 570, DIN 53122 part 1

### Uses

La GreenCote Plus system is suitable for use on all types of concrete structures which are directly exposed such as Buildings, Bridges, Flyovers and Under-passes. Also Suitable for application on previously painted surfaces.

### Advantages

- **High Build Film** - Higher thickness ensures longevity
- **Elastomeric** - Accommodates thermal movement of hair-line cracks
- **UV Stability** - Resistance to UV rays
- **Anti-Dirt & Anti-Fungal**
  - Low dirt pick-up and can be cleaned easily
  - Resistance to Fungal and Algae
- **Anti-Carbonation** - Unique anti-carbonation property to protect structural reinforcement in concrete.
- **Breathability** - Allows internal moisture to escape
- **Ease of Application** - User friendly product and can be easily applied by brush, roller or spray

### Technical Properties

|   |                           |
|---|---------------------------|
| Specific Gravity  | 1.25±0.05                 |
| Adhesion to concrete ASTM D4541                                     | 3.7N/mm <sup>2</sup>      |
| Water absorption ASTM D 570   | 0.8%                      |
| Resistance to chloride,   | Good                      |
| UV resistance (1000 hrs) ASTM G153                                  | Good                      |
| Resistance to algae & Fungi   | Good                      |
| Water Vapour Permeability (gm./m <sup>2</sup> /hrs)Test ASTMD1653   | 1.0                       |
| Diffusion resistance Carbon Dioxide Permeability (DIN 53122 part 1) | 4.46 g/(m <sup>2</sup> d) |
| Diffusion equivalent air layer thickness (Sp)                       | 55.7 m                    |
| Diffusion resistance number   | 22.3 μ                    |
| Dry Film thickness  | 120 microns in 2coats     |
| Elongation at 120 microns ASTM D882                                 | >330%                     |
| Tensile Strength ASTM D882  | 4.29 MPa                  |
| Shore 'A' Hardness  | 80                        |

### Application Instructions

#### Surface Preparation

All surface should be dry and free from contamination such as oil, grease, loose particles, decayed matter, moss, algae growth, laitance, and all traces of mould release oils and curing compounds. This is best achieved by thoroughly surface preparation.

It is essential to produce an unbroken coating of La GreenCote Plus water based system. To ensure this is achieved, surfaces containing cracks should first be filled using La CrackFill and spalled portion with polymer modified mortar using La Bond SBR/AR.

#### Priming

La Prime Cote is a water thinnable acrylic primer coating for external walls. It has excellent water repellent characteristics and hence provides water proofing properties to external walls.

- Prime the surface with La PrimeCote diluted with potable water by 25% (1Ltr of Primer and 250ml of Water) and allow it to dry for 2-3hrs

#### Applications

In order to obtain the protective properties of the La GreenCote Plus water based system, it is important that the correct rates of application and over coating time are observed.

### Mixing

Add maximum of 4 Ltrs clean water to the 20 litre container and mix thoroughly using a slow speed drill fitted with a paddle.

### La GreenCote Plus

|                               |                                 |
|-------------------------------|---------------------------------|
| Number of coat(s) Recommended | 2                               |
| Total dry film thickness      | min.120 microns                 |
| Over coating time             | @ 30 <sup>0</sup> C 5 - 6 hours |

Application should not commence if the temperature of the substrate is below 10<sup>0</sup>C or above 45<sup>0</sup>C

### Applications

All prepared substrates should be treated with two coats of La GreenCote Plus system. The material should be stirred well thoroughly before use. The first coat should be applied generously and worked into all hairline cracks and voids by the use of suitable brushes or rollers to achieve a uniform coating. This coat should be allowed to dry before applying the second coat. Always keep a 'wet edge' to avoid ridging and overspreading. Never stop in the middle of the wall and always complete one wall at a time. The second coat of La GreenCote Plus water based system must be applied exactly as detailed above.

La GreenCote Plus system can also be spray applied.

### Precautions & Limitations

- Do not dilute GreenCote Plus more than prescribed quantity as per datasheet.
- Do not apply if rain is expected within 12 hours of application
- Do not use on interior applications
- Do not use where there may be hydrostatic water transfer from the backside of the substrate
- Do not apply to improperly sealed substrates that are subject to raising dampness or moisture migration
- For extra protection, apply additional coat on rain lashing walls
- Over diluting GreenCote Plus like any other paint will effect the properties of the product

### Coverage

La GreenCote Plus covers 5-5.5m<sup>2</sup>/Litre in 2 coats on primed surface.

La PrimeCote covers 8-10m<sup>2</sup>/Litre in single coat

### Package

La GreenCote Plus is available in

|                    |                       |
|--------------------|-----------------------|
| White & Light Base | : 4 & 20 Litre Cans   |
| Dark Bases         | : 3.8 & 19 Litre Cans |
| La PrimeCote       | : 20 Litre Can        |

### Shelf Life

18 months if stored in original packing under shed and at normal ambient temperature

### Health & Safety

La GreenCote Plus is toxic and should not be swallowed or allowed to come into contact with skin and eyes. Wear suitable protective gloves and goggles. Splashes on the skin should be removed with water. Incase of contact with eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

### Fire

La GreenCote Plus is water based and non-flammable but should be stored away from combustible materials.

**Important:** La Greens India Pvt. Ltd., products are guaranteed against defective materials and are sold subject to its standard terms and conditions of sale. It is the Customer's responsibility to satisfy themselves by checking with the Company whether the information is still current at the time of use. The customer must be satisfied that the product is suitable for the use intended. All products comply with the properties shown on current Technical Literatures. However, La Greens India does not warranty or guarantee the installation of the products as it does not have any control over installation or end use of the product. All information and particularly the recommendation relating to application and end use are given in good faith.



**La Greens India Pvt. Ltd.**  
(Formerly Known as Lacrete Durakem (India) Pvt. Ltd.)  
No.136, SLV Arcade, 2<sup>nd</sup> Floor, 1<sup>st</sup> K Block,  
Dr. Rajkumar Road, Rajaji Nagar, Bangalore 560 010.

+91 80 4157 1956 ✉ info@lagreensindia.com 🌐 www.lagreensindia.com

**Manufacturing Unit :**  
Plot No.154, KIABD Indl. Area, 2<sup>nd</sup> Phase,  
Antharasanahalli, Tumkur - 572106, Karnataka

