

### Product Description

La CureCrete R is a aluminized resin based, liquid membrane curing compound for concrete. Conforms to BS:7542-1992, ASTM: C309.

### Uses

- Improved curing of concrete enhances cement hydration and provides a more durable concrete
- Control of moisture loss improves surface quality, reducing permeability, producing a hard-wearing, dust free surface and minimising potential for surface cracking and shrinkage
- Spray application reduces labour costs and eliminates the need for alternative curing systems.
- White metallic colour helps quality controllers at job site to ensure that full area is covered.
- Solar refractive

### Grades

La CureCrete R for general interior floor use & exterior pavement grade concrete.

### Specification

Concrete surfaces shall be cured by a liquid membrane material conforming to ASTM C309-58, such as La CureCrete R as supplied by La Greens. Material to be applied strictly in accordance with manufacturer's instruction.

### Recommended System

One full coat until a continuous, uniform film has been achieved.

### Application Instructions

Pigmented grades should be stirred before use to ensure even dispersion of pigment. La CureCrete R should be spray applied to the surface of fresh concrete. Application should begin as soon as the concrete is free from surface water. Do not apply if bleed water is forming or present on the concrete surface.

The spray nozzle should be held approximately 450mm from the concrete surface and passed back and forth to ensure complete coverage. Pump pressure should be maintained to give an even, fine spray.

After spraying, no further application of water or other material is necessary to ensure continued curing. The concrete surface should not be disturbed until it has sufficient strength to bear surface loads. The applied film should not be walked on before it is fully dry and care should be taken to ensure that the film is not broken.

La CureCrete R may also be applied to the surface of newly hardened concrete immediately after demoulding. In such cases the concrete surface should be sprayed with water to saturate it prior to the application of La CureCrete R. Dry surfaces may prevent correct film formation and cause absorption of the La CureCrete R which may lead to staining and difficulty in later removal.

### Application Data

**Application Equipment** : Low pressure spray, roller of soft brush

**Cleaning** : Mineral Turpentine

### Technical Properties

<b>Temperature</b>	May be applied at all temperatures.
<b>Specific Gravity</b>	0.97±0.01
<b>Thinning</b>	Not Required
<b>Coverage / Dose Rate</b>	Will vary depending on texture of surface and spray methodology and spray equipment. Coverage is 5 - 7m <sup>2</sup> /litre
<b>Drying Time</b>	Approx. 1½ hours @25° C
<b>Toxicity</b>	If swallowed seek medical advice.
<b>Type</b>	Resin based compound with Aluminium pigments

## Testing

La CureCrete R meets the requirements of ASTM C-309 for moisture retention in liquid membrane curing compounds also it complies BS:7542-1992 for curing efficiency.

## Shelf Life

If stored in unopened containers, under shade and at normal ambient temperature, a shelf-life of approximately 06 months could be expected.

## Package

La CureCrete R is available in 20 and 200 Ltr Steel Drum or Poly Carbuoy.

**Important:** La Greens India Pvt. Ltd., products are guaranteed against defective materials and are sold subject to its standard terms and conditions of sale. It is the Customer's responsibility to satisfy themselves by checking with the Company whether the information is still current at the time of use. The customer must be satisfied that the product is suitable for the use intended. All products comply with the properties shown on current Technical Literatures. However, La Greens India does not warranty or guarantee the installation of the products as it does not have any control over installation or end use of the product. All information and particularly the recommendation relating to application and end use are given in good faith.



### La Greens India Pvt. Ltd.

(Formerly Known as Lacrete Durakem (India) Pvt. Ltd.)  
No.136, SLV Arcade, 2<sup>nd</sup> Floor, 1<sup>st</sup> K Block,  
Dr. Rajkumar Road, Rajaji Nagar, Bangalore 560 010.

+91 80 4157 1956 ✉ info@lagreensindia.com 🌐 www.lagreensindia.com

### Manufacturing Unit :

Plot No.154, KIABD Indl. Area, 2<sup>nd</sup> Phase,  
Antharasanahalli, Tumkur - 572106, Karnataka



An ISO : 9001 Accredited Company